

SCIENTIFIC NAME

Tarrietia utilis

LOCAL NAME

Anguekong, Kwaeduma



Profile

The tree reaches a height of 32 to 43 m. The bole is straight and clear to 20 m in length, buttressed and sometimes irregular or stilt rooted in swampy areas. The trunk diameter attains 70 to 100 cm.

FAS Grade Sawn Hardwood Timber:

- FAS Grade Sawn Hardwood
- Air Dried / Kiln Dried
- Thickness=25/30/42/50/75/100/130mm
- Width=150mm up (10%)
- Length=2m up (5%)

Specification

Strength:

Medium

Natural:

Durability Moderate/High

Shrinkage:

Medium

Movement in Service:

Medium

Forest Availability:

Average

Forest Availability:

Average

Sawing:

Moderate/Easy

Machining:

Reportedly easy

Finishing:

n/a

Fixing:

n/a

Characteristics:

Commercial redwood of durability and strength

Uses:

veneer, vehicle bodies, plywood, joinery - exterior, furniture, frames, doors, boat construction

Weight:

Medium-Heavy 625kg/m³ at 12-15% moisture content.

