

SCIENTIFIC NAME

Celtis mildbraedii = C.zenkeri

LOCAL NAME

Asan, Ba, Celtis, Esa-fufuo



Profile

Celtis trees can reach up to 45 m, with straight and cylindrical boles, up to 100 cm of diameter. The buttresses are absent or up to 3 m high.

FAS Grade Sawn Hardwood Timber:

- FAS Grade Sawn Hardwood
- Air Dried / Kiln Dried
- Thickness=25/30/42/50/75/100/130mm
- Width=150mm up (10%)
- Length=2m up (5%)

Specification

Strength:

Medium

Natural:

Durability Low

Shrinkage:

Medium

Movement in Service:

n/a

Forest Availability:

Abundant

Forest Availability:

Abundant

Sawing:

n/a

Machining:

n/a

Finishing:

n/a

Fixing:

n/a

Characteristics:

Strong light coloured structural wood

Uses:

exterior use (with preservative treatment), furniture, handles, plywood, veneer, mouldings, flooring, trim - interior, joinery - interior

Weight:

Heavy 750kg/m³ at 12-15% moisture content.

