

SCIENTIFIC NAME

Turreanthus africanus

LOCAL NAME

Apapaye, Apaya, Engan



Profile

Avodire can exhibit a range of grain patterns, such as wavy, mottled, and rippled, with an almost-shimmering chatoyance, making it a popular choice for veneering applications.

FAS Grade Sawn Hardwood Timber:

- FAS Grade Sawn Hardwood
- Air Dried / Kiln Dried
- Thickness=25/30/42/50/75/100/130mm
- Width=150mm up (10%)
- Length=2m up (5%)

Specification

Strength:

Low/Medium

Natural:

Durability Low

Shrinkage:

Medium

Movement in Service:

Small

Forest Availability:

Average

Forest Availability:

Average

Sawing:

Easy

Machining:

Reportedly easy

Finishing:

n/a

Fixing:

n/a

Characteristics:

Attractive pale silky wood for interior decorative panelling and furniture

Uses:

veneer and plywood - decorative, furniture, mouldings, fittings, joinery - high quality interior

Weight:

Medium 550kg/m³ at 12-15% moisture content.

